



RAHA GROUP

TECHNICAL DATA SHEET OF BITUMEN PENETRATION GRADE 60/70

BITUMEN 60/70	TEST METHOD	UNIT	RANGE	
			Min	Max
Softening point	ASTM D36	°C	46	-
Penetration Point at 25°C	ASTM D5	0.1mm	60	70
Ductility at 25°C, 5cm/min	ASTM D113	cm	100	-
Solubility in Trichloroethylene	ASTM D2042	%	99	-
Spot test	A.A.S.H.T.O T102	-	Negative	
Flash Point	ASTM D92	°C	230	-
After thin-film oven test				
Change of Mass	ASTM D1754	%	-	0.8
Retained Penetration	ASTM D5	%	52	-
Ductility, 5cm/min	ASTM D113	cm	50	-

PACKING:

- Bulk
- 180 kg New Steel Drum



No. 2305, Burlington Tower
Business Bay, DUBAI-UAE



+ (971) 4 566 4998
+ (971) 56 281 7292



www.rahaoil.ae



info@rahaoil.ae