



RAHA GROUP

TECHNICAL DATA SHEET OF BITUMEN PENETRATION GRADE 120/150

BITUMEN 120/150	TEST METHOD	UNIT	SPECIFICATION
Specific gravity @ 25°C	ASTM D70	kg/cm ³	1.000/ 1.050
Penetration @ 25°C	ASTM D5	mm/10	120/150
Softening point °C	ASTM D36	°C	38 min
Ductility @25 °C	ASTM D113	cm	100 min
Loss on heating(wt) %	ASTM D6	wt %	0.5 max
Drop in penetration after heating %	ASTM D5-D6	%	20 max
Flashpoint °C	ASTM D92	°C	218 min
Solubility in Trichloroethylene	ASTM D2042	wt %	99 max
Spot test	A.a.s.h.o.t102	-	Negative

PACKING:

Bulk
180 kg New Steel Drum



No. 2305, Burlington Tower
Business Bay, DUBAI-UAE



www.rahaoil.ae



+ (971) 4 566 4998
+ (971) 56 281 7292



info@rahaoil.ae