



RAHA SADR INDUSTRIAL CO

TECHNICAL DATA SHEET OF OXIDIZED BITUMEN 105/15

BITUMEN 105/5	TEST METHOD	UNIT	SPECIFICATION
Specific gravity @ 25/25 °c	ASTM D70	Kg/cm ³	1.05 approx
Penetration @ 25°C	ASTM D5	mm/10	10/20
Softening point °c	ASTM D36	°C	100/110
Loss on heating(wt) %	ASTM D6	wt %	0.2 max
Flashpoint °c	ASTM D92	°C	250 min
Solubility is CS2(wt) %	ASTM D4	wt %	99.5 max
Spot test	A.A.S.H.O.T102	-	Negative

Packing of Oxidized Bitumen 105/15

RAHA Group is the manufacturer of Blown Bitumen 105/15 in various packing, including bitumen 105/15 is available in 20 & 50 Kg Kraft Paper Bags / Poly Amide Bags, 25 Kg Carton box & 150, 180, 200kg Steel Drums. In addition, oxidized bitumen packing also palletize, 40 bags can stack on the pallet. 20 pallet can load to the 20ft container.



Unit303,Navab Complex,
Navab Safavi St.,Esfahan-Iran



+983132355207
+983132355214



info@rahaoil.com



www.rahaoil.com