



RAHA SADR INDUSTRIAL CO

TECHNICAL DATA SHEET OF OXIDIZED BITUMEN 105/35

BITUMEN 105/35	TEST METHOD	UNIT	SPECIFICATION
Specific gravity @ 25/25 °C	ASTM D70	Kg/cm ³	1.05 approx
Penetration @ 25°C	ASTM D5	mm/10	30/40
Softening point °C	ASTM D36	°C	100/110
Loss on heating(wt) %	ASTM D6	wt %	0.2 max
Flashpoint °C	ASTM D92	°C	250 min
Solubility is CS2(wt) %	ASTM D4	wt %	99.5 max

Packing of Oxidized Bitumen 105/35

RAHA GROUP is the manufacturer of oxidized Asphalt 105/35 in various packing, including bitumen 105/35 is available in 20 & 50 kg Kraft Paper Bags / Poly Amide Bags, 25 kg Carton box & 150, 180, 200 Kg Steel Drums. In addition, oxidized bitumen packing also palletize, 40 bags can stack on the pallet. 20 pallet can load to the 20ft container.

Sincerely
RAHA GROUP



Unit303,Navab Complex,
Navab Safavi St.,Esfahan-Iran



+983132355207
+983132355214



info@rahaoil.com



www.rahaoil.com