



RAHA SADR INDUSTRIAL CO

TECHNICAL DATA SHEET OF OXIDIZED BITUMEN 110/30

BITUMEN 110/30	TEST METHOD	UNIT	SPECIFICATION
Specific gravity @ 25/25 °C	ASTM D70	Kg/cm ³	1.05 approx
Penetration @ 25°C	ASTM D5	mm/10	10/25
Softening point °C	ASTM D36	°C	100/120
Loss on heating(wt) %	ASTM D6	wt %	0.2 max
Flashpoint °C	ASTM D92	°C	230 min
Solubility is CS2(wt) %	ASTM D4	wt %	99 max
Ductility @ 25 °C	ASTM D113	-	2 min

Packing of Oxidized Bitumen 110/30

RAHA Group is the manufacturer of Blown Bitumen 110/30 in various packing, including bitumen 110/30 is available in 20 & 50 Kg Kraft Paper Bags / Poly Amide Bags, 25 Kg Carton box & 150, 180, 200kg Steel Drums. In addition, oxidized bitumen packing also palletize, 40 bags can stack on the pallet. 20 pallet can load to the 20ft container.



Unit303,Navab Complex,
Navab Safavi St.,Esfahan-Iran



+983132355207
+983132355214



info@rahaoil.com



www.rahaoil.com