



RAHA SADR INDUSTRIAL CO

TECHNICAL DATA SHEET OF OXIDIZED BITUMEN 115/15

BITUMEN 115/15	TEST METHOD	UNIT	SPECIFICATION
Specific gravity @ 25/25 °c	ASTM D70	Kg/cm ³	1.05 approx
Penetration @ 25°C	ASTM D5	mm/10	10/20
Softening point °c	ASTM D36	°C	110/120
Ductility @25 °c	ASTM D113	Cm	1.5 min
Loss on heating(wt) %	ASTM D6	wt %	0.2 max
Flashpoint °c	ASTM D92	°C	250 min
Solubility is CS2(wt) %	ASTM D4	wt %	99.5 max
Spot test	A.a.s.h.o.t102	-	Negative

Packing of Oxidized Bitumen 115/15

RAHA Group is the manufacturer of Blown Asphalt 115/15 in various packing, including bitumen 115/15 is available in 20 & 50 Kg Kraft Paper Bags / Poly Amide Bags, 25 Kg Carton box & 200 Kg Steel Drums.



Unit303,Navab Complex,
Navab Safavi St.,Esfahan-Iran



+983132355207
+983132355214



info@rahaoil.com



www.rahaoil.com