



RAHA SADR INDUSTRIAL CO

## TECHNICAL DATA SHEET OF OXIDIZED BITUMEN 150/5

| BITUMEN 150/5               | TEST METHOD    | UNIT   | SPECIFICATION |
|-----------------------------|----------------|--------|---------------|
| Specific gravity @ 25/25 °c | ASTM D70       | Kg/cm3 | 1.05 approx   |
| Penetration @ 25°C          | ASTM D5        | mm/10  | 4/6           |
| Softening point °c          | ASTM D36       | °C     | 145/155       |
| Ductility @25 °c            | ASTM D113      | Cm     | 1.5 min       |
| Loss on heating(wt) %       | ASTM D6        | wt %   | 0.2 max       |
| Flashpoint °c               | ASTM D92       | °C     | 250 min       |
| Solubility is CS2(wt) %     | ASTM D4        | wt %   | 99.5 max      |
| Spot test                   | A.a.s.h.o.t102 | -      | Negative      |

### Packing of Oxidized Bitumen 150/5

RAHA GROUP is the manufacturer of oxidized bitumen 150/5 in various packing, including bitumen 150/5 is available in 20 & 50 Kg Kraft Paper Bags / Poly Amide Bags, 25 Kg Carton box & 150, 180 & 200 kg Steel Drums.



Unit303,Navab Complex,  
Navab Safavi St.,Esfahan-Iran



+983132355207

+983132355214



info@rahaoil.com



www.rahaoil.com