



RAHA SADR INDUSTRIAL CO

TECHNICAL DATA SHEET OF OXIDIZED BITUMEN 95/25

BITUMEN 95/25	TEST METHOD	UNIT	SPECIFICATION
Specific gravity @ 25/25 °C	ASTM D70	Kg/cm3	1.05 approx
Penetration @ 25 °C	ASTM D5	mm/10	20/30
Softening point °C	ASTM D36	°C	90/100
Ductility @ 25 °C	ASTM D113	Cm	1.5 min
Loss on heating (wt) %	ASTM D6	wt %	0.2 max
Flashpoint °C	ASTM D92	°C	250 min
Solubility in CS ₂ (wt) %	ASTM D4	wt %	99.5 max

Packing of Oxidized Bitumen 95/25

RAHA GROUP is the manufacturer of Oxidized Bitumen 95/25 in various packing, including bitumen 95/25 is available in 20 & 50 kg Kraft Paper Bags / Poly Amide Bags, 25 kg Carton box and 150, 180, 200kg Steel Drums. In addition, oxidized bitumen packing also palletize, 40 bags can stack on the pallet. 20 pallet can load to the 20ft container.



Unit303,Navab Complex,
Navab Safavi St.,Esfahan-Iran



+983132355207
+983132355214



info@rahaoil.com



www.rahaoil.com