RAHA SADR INDUSTRIAL CO

# TECHNICAL DATA SHEET OF OXIDIZED BITUMEN 85/35

| BITUMEN 85/35 | TEST METHOD | UNIT | SPECIFICATION |
|---|---|---|---|
| Specific gravity @ 25/25 °C | ASTM D70 | Kg/cm3 | 1.05 approx |
| Penetration @ 25 °C | ASTM D5 | mm/10 | 30/40 |
| Softening point °C | ASTM D36 | °C | 80/90 |
| Ductility @ 25 °C | ASTM D113 | Cm | 1.5 min |
| Loss on heating (wt) % | ASTM D6 | wt % | 0.2 max |
| Flashpoint °C | ASTM D92 | °C | 250 min |
| Solubility is CS2 (wt) % | ASTM D4 | wt % | 99.5 max |
| Spot test | A.A.S.H.O.T102 | - | Negative |

**Packing of Oxidized Bitumen 85/35**

**RAHA Group** is the manufacturer of Oxidized Bitumen 85/35 in various packing, including bitumen 85/35 is available in 20 & 50 kg Kraft Paper Bags / Poly Amide Bags, 25 kg Carton box and 150, 180, 200kg Steel Drums. In addition, oxidized bitumen packing also palletize, 40 bags can stack on the pallet. 20 pallet can load to the 20ft container.

Sincerely
RAHA Group

Unit303,Navab Complex,
Navab Safavi St.,Esfahan-Iran
+983132355207
+983132355214
info@rahaoil.com
www.rahaoil.com