RAHA SADR INDUSTRIAL CO

TECHNICAL DATA SHEET OF OXIDIZED BITUMEN 75/25

BITUMEN 75/25	TEST METHOD	UNIT	SPECIFICATION
Specific gravity @ 25/25 °C	ASTM D70	Kg/cm3	1.05 approx
Penetration @ 25 °C	ASTM D5	mm/10	20/30
Softening point °C	ASTM D36	°C	70/80
Loss on heating (wt) %	ASTM D6	wt %	0.2 max
Flashpoint °C	ASTM D92	°C	250 min
Solubility is CS2 (wt) %	ASTM D4	wt %	99.5 max
Spot test	A.A.S.H.O.T102	-	Negative

Packing of Oxidized Bitumen 75/25

RAHA Group is the manufacturer of Oxidized Bitumen 75/25 in various packing, including bitumen 75/25 is available in 20 & 50 kg Kraft Paper Bags / Poly Amide Bags, 25 kg Carton box and 150, 180, 200 kg Steel Drums. In addition, oxidized bitumen packing also palletize, 40 bags can stack on the pallet. 20 pallet can load to the 20ft container.

Sincerely
RAHA Group

Unit303,Navab Complex,
Navab Safavi St.,Esfahan-Iran
+983132355207
+983132355214
info@rahaoil.com
www.rahaoil.com